

TECHNICAL DATA SHEET SICO PRO 246-XXX

INTERIOR LATEX PAINT

Water-based product, pearl finish

Product Description

Interior latex paint with a pearl finish, ideal for use on properly prepared, interior walls, ceilings, doors, or trim composed of primed or previously painted drywall, plaster, masonry, wood, and metal.

Advantages

Durable.

- Good flow and levelling.
- High hiding.
- Easy to apply.
- Water-based product which allows tool clean-up with water.

Available Colours

 246-550
 White

 246-421
 Base 1*

 246-422
 Base 2*

 246-423
 Base 3*

*Must be tinted before use

Refer to the appropriate colour formula book, automatic tinting equipment, and/or computer colour-matching system for colour formulas and tinting instructions.

Projects

Environment

Interior only.

Use

New and maintenance work.

Residential and commercial sites.

Walls, doors and trim where a washable finish is required; particularly for living room, children's rooms, playrooms, hallways, laundry, dining room and kitchen.

Surfaces

Ideal for use on properly prepared, interior walls, ceilings, doors, or trim composed of primed or previously painted drywall, plaster, masonry, wood, and metal.

Notes

It is recommended to use a finish with a lower gloss on ceilings, particularly on living room, dining room and master bedroom ceilings.

Some colours, or drastic colour changes, may require additional coats of paint.

Do not apply directly over steel, iron or other metals.

Not formulated to be used on floors.

Do not mix with other paints or thinners.

Technical Specifications (21°C (70°F))

Appearance

Opaque

Gloss Level

Pearl finish

Gloss at 60°: 17 to 27%
Gloss at 85°: Not available

Composition

Diluent: WaterBinder: Vinyl Acrylic

Drying Time*

Touch dry:

Before recoating:
Full curing:

1 to 2 hours
4 to 6 hours
30 days

If relative humidity is higher than 50%, required time must be doubled.

Drying times listed may vary depending on temperature, humidity, colour, film build, and air movement.

Spreading Rate per Coat

3.78 L: 44 to 52 m² (480 to 560 ft²)

Coverage figures do not include material loss due to application. Some colours, drastic colour changes, or porous surfaces may require additional coats of paint to achieve a uniform finish.

Volatile Organic Compounds (VOCs)*

According to ASTM D3960-05: < 150 g/L

Solids by Volume*

32.9% (± 1%)

Flammability

Non flammable

Minimal Film Thickness*

(According to the maximum spreading rate)

Wet: 2.9 mils (73 μm)
Dry: 0.9 mil (24 μm)

Certifications*

Not available

*Technical data source: 246-550

Satisfaction Guaranteed

The manufacturer warrants your complete satisfaction with the performance of this product for as long as you own or reside in your home when our product has been applied and maintained according to label directions. This satisfaction guarantee is non-transferable. The manufacturer does not warrant against problems with the product which are caused by factors beyond its control, such as structural defects, damage to the coating film by others, poor condition of the substrate, improper application, etc. If not satisfied as warranted, return the unused portion along with sales receipt to place of purchase. You will receive as your exclusive remedy either a refund of the price paid for the product or replacement with product of equal value. This warranty specifically excludes labour or costs of labour for the removal or application of any coating and indirect, special, consequential, and incidental damages.



Surface Preparation

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks or open seams. Sand all glossy, rough, and patched surfaces.

In order to prepare surfaces adequately, follow the preparation steps, as described below:

- ▶ Clean with an appropriate cleaner for removing the contaminant. Remove mildew with a solution of household bleach (1 part household bleach to 3 parts of water). Wear rubber gloves and eye protection.
- Rinse thoroughly with clear water and let dry completely.
- Strip, scrape or remove all loose and peeling paint, and sand to smooth edges.
- Sand rough areas and dull glossy surfaces. Eliminate sanding residues. Touch up bare spots.
- Repair holes and cracks with an appropriate filler.
- If wood exudes resin, scrape the excess and clean surface with alcohol or paint thinner. On bare wood, seal knots and sap streaks with shellac before applying the primer.
- Cover or mask surfaces that are not to be painted.

Listed below are the main base coat products that are recommended:

- Primers: Prime all bare wood, gypsum, plaster, masonry, metal, and porous surfaces with an appropriate primer.
- Bare wood: Seal knots and sap streaks with shellac. Prime with Sico Pro 240-125 or GoPrime 200-135. On woods rich in tannins, such as cedar or redwood, use GoPrime
- Gypsum boards and drywall joint compound: Sico Pro 240-125 or 240-140.
- Concret, Stucco, or Masonry: Plaster, concrete, and masonry must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. Remove surface dust and prime entire surface prior to painting.
- New or bare ferrous metal (iron, steel): Corrostop Ultra 635-060 or 635-085.
- New galvanized metal: Corrostop Ultra 635-045 or GoPrime 190-135.
- Previously painted latex surfaces in good condition: No primer is required.
- Previously painted alkyd surfaces in good condition: Prime surface with an appropriate primer.

Recommendations

Application Conditions

Temperature: 10 to 32°C (50 to 90°F)

Relative humidity: Ideal between 15 and 55%,

maximum 85%.

Maintain these conditions during the application and the following 24 hours. Low temperature, high humidity, thick films or poor ventilation extend drying time.

- Paintbrush: Synthetic bristles (nylon, polyester).
- Roller: 10 mm (3/8 in.).
- *Spray (airless equipment)
- Tip size: 0.015 to 0.021 in.;
- Pressure: 1500 to 2000 psi.

Always use top quality application tools.

*Spray recommendations may vary from figures listed depending on equipment manufacturer.

Cleaning Tools

Clean tools with warm, soapy water.

Storage and Transportation

Keep product in a dry area between 10 and 30°C (50 and 86°F)

PROTECT FROM FREEZING.

Disposal

Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment. Do not pour down a drain or storm sewer.

Application

information.

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours, spray or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. FIRST AID TREATMENT: If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: titanium dioxide; limestone; propane-1,2-diol; kaolin. Keep container tightly closed and sealed until ready for use. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426. EMERGENCY SPILL INFORMATION: 514-645-1320.

PRECAUTION: Dry sanding will give rise to dust and/or hazardous fumes. Wear suitable respiratory protective equipment. WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact a regional Health Canada office for more

For more information, visit the website at www.sico.ca or call our customer service: 1-800-463-7426.

Safety Measures

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours, spray or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID TREATMENT: If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: titanium dioxide; Limestone; propane-1,2diol; Kaolin; diatomaceous earth; nepheline syenite; talc, not containing asbestiform fibres. Contains isothiazolinones. May cause allergic reaction. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426 (Canada). EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.), (514) 645-1320 (Canada).

Surface Maintenance

- Wait for its full curing before washing the product or testing its adhesion: minimum 30 days (longer in conditions of high humidity or low temperature). Use a non-abrasive, mild cleaner and a soft cloth.
- If required, touch up bare areas with primer and apply another coat on the whole surface.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-866-660-2220.



1550 rue Ampère, Suite 500 Boucherville (Québec), J4B 7L4

PPG Architectural Coatings Canada, Inc. The PPG logo is a registered trademark of PPG Industries Ohio, Inc. Sico is a registered trademark and Sico Pro is a trademark of the PPG Architectural Finishes, Inc.